



CROHMIQ® Static Protective FIBC Fabric

"3 oz" Fabric

TYPICAL DATA SHEET

<u>Typical Properties</u>	<u>Test Method</u>	
• Material		Polypropylene
• Coating ⁽¹⁾		Homo PP/LDPE/LLDPE, clear
• Color		White with blue highlight yarns
• Standard Widths ⁽²⁾ (± 0.5 in. / ± 1.3 cm)	ASTM D-3774	Inches: 20, 42, 45, and 48 cm: 51, 107, 114 and 122
• Construction ⁽³⁾	ASTM D-3775	10 ends/in. × 10 picks/in. 39 ends/10 cm × 39 picks/10 cm
• Minimum Weight	ASTM D-3776	2.4 ± 0.12 oz/yd ² Uncoated 81 ± 4 g/m ² Uncoated 3.1 ± 0.16 oz/yd ² Coated 105 ± 5.25 g/m ² Coated
• Tensile Strength ⁽³⁾	ASTM D-4632	100 lbf × 100 lbf 445 N × 445 N
• Elongation ⁽³⁾	ASTM D-4632	20 %
• UV Resistance, Strength Retention	ASTM D-4355	>70% after 1200 hrs exposure

(1) CROHMIQ® static protective Type D FIBC fabrics may be used as intended for bulk storage or transport of dry food, and such use may properly be said to comply fully with the Federal Food, Drug and Cosmetic Act and EU Directive 2002/72/EC for Plastic Materials & Articles Coming into Contact with Food.

(2) Custom widths and tucked edges are available, subject to minimum order quantity.

(3) The above properties are typical averages based upon uncoated test data only.

Effective Date: October 20, 2010. This data sheet supersedes all previously issued data sheets and is valid only for fabric manufactured after the effective date.

TEXENE is a trademark of TEXENE LLC, Summerville, SC, USA.
CROHMIQ, CROHMIQ blue, CROHMIQ white and the blue fabric color are additional trademarks of TEXENE LLC.
US patents 5,478, 154; 5,679,449 and 6,112,772, and additional foreign patents and patent pending.

©2010 TEXENE LLC.

All Rights Reserved.

The information on this data sheet relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. No representation, warranty, or guarantee, however, is made as to the accuracy, reliability, or completeness. Nothing herein shall be construed as creating any express or implied warranty, including but not limited to any implied warranty of merchantability or implied warranty of fitness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. TEXENE LLC does not accept liability for any loss or damage that may occur from the use of this information.