



Effective Date: **October 11, 2021**

CROHMIQ® Static Protective FIBC Fabric

“6.5 oz” Fabric

TYPICAL DATA SHEET

<u>Typical Properties</u>	<u>Test Method</u>	
• Material ⁽¹⁾		Polypropylene
• Coating ⁽¹⁾		Homo PP/LDPE/LLDPE, clear
• Color		Blue / 1 - Red Marker
• Standard Widths ⁽²⁾ (± 0.5 in. / ± 1.3 cm)	ASTM D-3774	Inches: 42, 45, and 48 cm: 107, 114 and 122
• Construction ⁽³⁾	ASTM D-3775	9.6(2) ends/in. x 12 picks/in. 38 ends/10 cm x 47 picks/10 cm
• Weight ⁽³⁾	ASTM D-3776	6.5 ± 0.33 oz/yd ² Uncoated 220 ± 11 g/m ² Uncoated 7.4 ± 0.37 oz/yd ² Coated 252 ± 12.7 g/m ² Coated
• Tensile Strength ⁽³⁾	ASTM D-4632	300 lbf x 300 lbf 1334 N x 1334 N
• Elongation ⁽³⁾	ASTM D-4632	25 %
• UV Resistance, Strength Retention	ISO 21898	>50% after 200 hours exposure

(1) CROHMIQ® static protective Type D FIBC fabrics are suitable for food contact applications as components of FIBC manufactured as directed in Technical Note 131.

(2) Custom widths and tucked edges are available, subject to minimum order quantity.

(3) The above properties are typical averages based upon uncoated test data only.

This data sheet supersedes all previously issued data sheets and is valid only for fabric manufactured after the effective date.

TEXENE is a trademark of TEXENE LLC, Miami Lakes, FL USA.

CROHMIQ, CROHMIQ blue, CROHMIQ white and the blue fabric color are additional trademarks of TEXENE LLC.

US patents 9,815,618; 9,611,091; 9,815,619 and 10,023,380, and additional foreign patents and patent pending.

©2011-2021 TEXENE LLC.

All Rights Reserved.

The information on this data sheet relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any other process. Such information is, to the best of our knowledge and belief, accurate and reliable as of the date compiled. No representation, warranty, or guarantee, however, is made as to the accuracy, reliability, or completeness. Nothing herein shall be construed as creating any express or implied warranty, including but not limited to any implied warranty of merchantability or implied warranty of fitness. It is the user's responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. TEXENE LLC does not accept liability for any loss or damage that may occur from the use of this information.